

PRODUCT DATA SHEET



SINCE 1936

#7100

EVERBOND CONCRETE PRIMER

DESCRIPTION

EVERBOND CONCRETE PRIMER is specially formulated to provide superior alkali and efflorescence resistant coating on cementitious surfaces. Recommended for new and aged concrete, block, stucco, and plaster. Maybe applied to untreated concrete, stucco.

USE

Residential or commercial use.

Exterior/Interior. Stucco, concrete, concrete tilt-up, masonry, and plaster compatibility.

COLOR: White

FINISH: Flat

Viscosity@77 F: 105-110 KU

Weight per gallon: 10.5 Lbs/Gal

Solid by Volume: 32.0 \pm 2%

Solid by Weight: 46.2 \pm 2%

Recommended film thickness per coat:

Wet: 4.5 mils **Dry:** 1.5 mils

COVERAGE: 300 to 350 sq. ft. per gallon.

Actual coverage may vary due to surface conditions and applying technique.

THINNING: This product is formulated to be used at package consistency. However, if thinning is required, add water sparingly for good flow and workability.

DRYING TIME: Dry to touch in 2 hours. Recoat in 4 hour. Actual drying time may vary due to temperature and humidity.

SURFACE PREPARATION

New work: All surfaces must be clean, dry and free of dust, rust, dirt, stains, mildew, grease, wax, oil, efflorescence or other foreign materials that could cause adhesion problems. Allow concrete or stucco to cure before application of primer and finish coats.

Pre treat all galvanized, non ferrous metal, newly poured or pre casted concrete surfaces. Patch all voids, cracks, and holes with appropriate patching or caulking materials. New surfaces should be sealed with suitable primer/sealer.

Old work: Power wash, scrape, sand and completely clean to remove any dirt, rust, chalk, grease, oil, wax, loose paint or any other foreign materials. Glossy surfaces should be dulled down for good adhesion.

Concrete Tilt Up: If bond breakers, parting agents, form oils or curing compounds has been used, test the surface for

Concrete, Masonry: The surface must cure 30-days before priming. Efflorescence deposits have to be neutralized with 10% solution of muriatic acid and rinsed thoroughly with water.

Warning– Special instructions

If you scrape, sand, or remove old paint of old buildings (especially pre 1978), you may release lead dust or asbestos dust. Exposure to lead dust and asbestos dust can cause serious illness, such as brain damage, lung cancer. Always wear proper personal protective equipment during surface preparation, and Finish cleanup of any residues. For more information, log on to www.epa.gov/lead or www.epa.gov/asbestos. Or contact at 1-800-424-LEAD.

APPLICATION

Brush, roll or spray. Do not apply this product when surface or air temperature is below 50 degrees Fahrenheit. Protect all surrounding areas from splash, over-spray and spill during application.

VOC: Less than 100 grams per liter

CLEAN-UP: Clean tools, equipment and area with soap and warm water.

MATERIAL SAFETY DATA SHEET

Available at www.tibbettpaint.com